

An inhibited high-grade oil, Nytro Lyra X conforms to IEC 60296 Ed. 5 (2020) and is Type A, declared as TVAL. Developed and formulated to deliver strong resistance to oil degradation, Nytro Lyra X provides excellent oxidation stability for a longer transformer life with less maintenance.

Designed for heavy duty

This product has been specially developed for use in oil-filled electrical equipment – including power and distribution transformers, rectifiers, circuit breakers and switchgears.

Performance and benefits

Very good heat transfer. Thanks to low viscosity and viscosity index, this high grade offers extremely good heat transfer characteristics, ensuring heat is efficiently removed from core and windings.

Excellent oxidation stability. Developed and formulated to deliver superb resistance to oil degradation, this grade provides excellent oxidation stability for enhanced transformer life and minimum maintenance.

Very good low temperature properties. Naphthenic characteristics allow the transformer to start at the lowest possible temperature – without using pour point depressants.

High dielectric strength. This insulating oil both meets and exceeds the toughest demands on dielectric strength – when stored and handled correctly.

Product description

Nytro Lyra X fulfils the requirements for IEC 60296 Ed 5.0 fully inhibited oil and it is 100% recyclable. Nynas classify this product as a high grade.

Nytro Lyra X is rigorously analysed and passes the following corrosion tests:

- ASTM D1275
- IEC 62535
- DIN 51353

In accordance with IEC 60296 Ed 5.0, all additives are declared.

There's more to us than this

We're delighted you chose one of our transformer oils. If you have any questions about other products and services, get in touch with your local Nynas contact. Besides top quality oils, we offer a wide range of services, including rapid delivery worldwide, sample analysis, training, seminars and much more. All you have to do is ask. Find out more at www.nynas.com

PROPERTY	Unit	Test Method	Specification Limits		Typical Data
			Min	Max	
1 - Function					
Viscosity, 40°C	mm ² /s (cSt)	ISO 3104		12	9.5
Viscosity, -30°C	mm ² /s (cSt)	ISO 3104		1800	895
Pour point	°C	ISO 3016		-40	-48
Water content	mg/kg	IEC 60814		30	< 20
Breakdown voltage	kV	IEC 60156			
- Before treatment	kV	IEC 60156	30		40-60
- After treatment	kV	IEC 60296	70		> 70
Density, 20°C	kg/dm ³	ISO 12185		0.895	0.861
DDF at 90°C		IEC 60247		0.005	< 0.001
2 - Refining/stability					
Colour		ISO 2049		< 0.5	< 0.5
Appearance at 15°C		IEC 60296	Clear, Free from Sediment		Clear, Free from Sediment
Acidity	mg KOH/g	IEC 62021		0.01	< 0.01
Interfacial tension at 25°C	mN/m	IEC 62961	43		48
Total sulphur content	%	ISO 14596		0.05	< 0.01
Corrosive sulphur		DIN 51353	Non-Corrosive		Non-Corrosive
Potentially corrosive sulphur		IEC 62535	Non-Corrosive		Non-Corrosive
Corrosive sulphur		ASTM D1275	Non-Corrosive		Non-Corrosive
DBDS	mg/kg	IEC 62697-1	Not Detectable		Not Detectable
Antioxidants	wt %	IEC 60666	0.08	0.40	0.38
Metal passivator additives	mg/kg	IEC 60666	Not Detectable		Not Detectable
Other additives *			None		None
2-Furfural and related compounds content	mg/kg	IEC 61198		< 0.05	< 0.05
Aromatic content	%	IEC 60590			5
Stray gassing under thermo-oxidative stress		IEC 60296			
- Hydrogen	µl/l	clause A.4		< 50	< 5
- Methane	µl/l	clause A.4		< 50	< 1
- Ethane	µl/l	clause A.4		< 50	< 1
3 - Performance					
Oxidation stability at 120°C, 500 h		IEC 61125			
- Total acidity	mg KOH/g	IEC 61125		0.3	0.05
- Sludge	wt %	IEC 61125		0.05	< 0.01
- DDF at 90°C		IEC 61125		0.050	0.006
4 - Health, safety and environment (HSE)					
Flash Point, PM	°C	ISO 2719	135		148
PCA	wt %	IP 346		< 3.0	< 3.0
PCB	mg/kg	IEC 61619	Not Detectable		Not Detectable

*this product contains no undeclared additives

NYTRO LYRA X is an inhibited insulating oil meeting IEC 60296 Ed. 5 (2020) Type A, TVAL and it is 100% recyclable. Breakdown voltage after treatment as per definition in IEC 60296, section 6,4

Severely hydrotreated insulating oil

Issuing date: 19-09-2023